



KING BAG & MANUFACTURING CO.
1500 spring lawn avenue / cincinnati, ohio 45223-1699 (513)541-5440
www.kingbag.com Fax (513)541-6555

Fiber

Polypropylene

Yarn Type - Warp

MONOFILAMENT

Yarn Type - Weft

MONOFILAMENT

Weight

(oz/yd²)

3.9

Weave Pattern

TWILL

Air Permeability

(CFM)

NA

Threads - Warp

(inch)

50

Threads - Weft

(inch)

50

Opening

(Micron)

300

Open Area

(%)

37

Finish

HEAT SET

Additional Guidance on Fiber - Polypropylene

- Good resistance to wear
- Very Good resistance to alkalis
- Very Good resistance to Hydrolysis
- Poor resistance to Oxidizing Agents
- Very Good resistance to strong acids
- Maximum operating temp 95°C